



OZ MOTUF

Design Description

Oz Motuf is a high strength engineering plastic suitable for bearings, bushing and back-up ring applications. This flexible bearing material provides increased thermal stability, elongation and abrasion resistance. It also displays good, low temperature impact resistance, high dimensional stability, favorable frictional properties (triple lubricated) and low water absorption.

Features
• High performance urethane plastic
• Thermoset polyurethane
• Low compression set
• Excellent hot water resistance
• Resistance in HFA, HFB hydraulic fluids and using biologically reducible hydraulic fluids
• Outstanding toughness & abrasion for high pressure applications
• Mineral oil compatibility is good
• Good resistance to ozone attack & weathering
• Low compression set, excellent hot water resistance, resistance in HFA/HFB and HFC hydraulic fluids and

Properties	Standard	Unit	Value
Hardness	DIN 53505	Shore D	85D
Density	DIN 53479	g/cm³	1.2
Tensile strength	DIN 53504	MPa	42
Elongation at break	DIN 53504	%	165
100% Modulus	DIN 53504	MPa	42
200% Modulus	DIN 53504	MPa	49.3
Compression set 70 °C/70h	DIN 53517	%	40
Tear strength: with nick	DIN 53515	KN/m	146
Abrasion loss	DIN 53516	mm³	102
Minimum application temperature		°C	-50
Maximum application temperature		°C	130
Swell in water		%	0.3-0.4 max
Thermal		Unit	Value
Melting Point		°C	216
Thermal Conductivity		W/M°C	0.25
Specific Heat		KJ/kg°C	1.67
Co-efficient of Linear Expansion		106/°	70-80
Safe Temp- Short Period		°C	180
Safe Temp- Continuous		°C	-150
Heat Distortion Temp (Martens)		°C	80





OZ MOTUF

Comparison of OZ MOTUF with varied bearing materials

	Loading Limit kg/cm ²	Thermal Expansion 105°C/cm/°C	Water Absorption	Friction Tests. Load = 0.86 KG/CM ²			
				Temper Rise of Steel Journal After 30 mins			
				No Lubrication		Initial Lubrication	
				50 Metres/Min	50 Metres/Min	160 Metres/Min	
PTFE Unfilled	50	17	0	24°C (worn)	15°C	-	
HD Polyurethane	100	25	0.01	22°C (seized)	14°C	Seized	
Nylon 6	200	9	9	28°C (seized)	15°C	Seized	
OZ Monyl	305	5	0.4	22°C	6°C	14°C	
Phosphor Bronze	800	1.8	0	38°C (worn)	20°C	69°C	

